

Disclosed is a method for polishing a surface of a substrate containing Ru or a Ru compound in a surface region, said method comprising a polishing step with a polishing liquid containing tetravalent cerium ions. The polishing liquid is prepared by adding a compound having a tetravalent cerium ion or its solution to a solvent in or immediately before the polishing step of the substrate.

5